

## AFINITICA® ADHESIVE WELDING METAL +

### PRODUCT DESCRIPTION

<b>Technology</b>	Cyanoacrylate
Chemical Type	Ethyl Cyanoacrylate
Appearance (Comp. A)	Clear gel
Appearance (Comp. B)	Grey gel
Appearance of Mix	Grey gel
Components	Two component - requires mixing
Viscosity	Thixotropic gel
<b>Cure</b>	By mixing

AFINITICA® Adhesive Welding Metal + is a gap filling instant adhesive with excellent bonding properties to a very broad range of materials and surfaces. This two-component formulation has been formulated to optimise bond strength on metal substrates, particularly aluminium. Aside from superior bonding to metal substrates, this product has excellent bonding properties to many other substrates – such as wood, plastic or glass. Curing time of only 5 minutes, working times (in-mixer) up to 7 minutes. The gel consistency allows application in any orientation whilst the static mixing nozzle ensures uniform and precise application for exceptional user convenience.

### TYPICAL PROPERTIES OF UNCURED MATERIAL

#### PART A:

Specific gravity, 25 °C, g/cm<sup>3</sup>: 1.07

Viscosity, 25 °C, mPa·s (cP):  
Spindle 14, speed 1.5 rpm: 100,000 – 200,000

Viscosity, 25 °C, mPa·s (cP):  
Spindle 14, speed 10 rpm: 20,000 – 35,000

#### PART B:

Specific gravity, 25 °C, g/cm<sup>3</sup>: 1.1

Viscosity, 25 °C, mPa·s (cP):  
Spindle 14, speed 1.5 rpm: 60,000 – 90,000

Viscosity, 25 °C, mPa·s (cP):  
Spindle 14, speed 10 rpm: 10,000 – 25,000

#### MIXED:

Open time at 25 °C: 5 – 7 minutes

Working time at 25 °C (in the static mixer):  
6-7 minutes

### TYPICAL CURING PERFORMANCE

Curing is initiated by mixing the Part A and Part B components. Handling strength is achieved rapidly; full strength is achieved within 24 hours.

### FIXTURE TIMES

Fixture time is the time at which an adhesive bond (250 mm<sup>2</sup>) is capable of supporting a 3 kg load for 10 seconds. The fixture time will depend on the substrate. The table below shows the fixture time for different substrates using lap shears.

	Time (s)
Beech Wood	20 – 50
ABS	40 – 70
Aluminium A5754	30 – 100
Aluminium A5083	35 – 90
Aluminium A6082	30 – 100
Mild Steel	10 – 40

### TYPICAL PERFORMANCE OF CURED MATERIAL

#### TENSILE SHEAR STRENGTH

The tensile shear strength will depend on the substrate. The Table below shows the shear strength for different substrates using lap shears according to ISO 4587.

Cured for 24h at 22°C

	Strength (N/mm <sup>2</sup> )
Beech Wood	13 – 16
ABS	8 – 10*
Aluminium A5754	19 – 22
Aluminium A5083	19 – 22
Aluminium A6082	21 – 23
Mild Steel	>24
GBMS	>24

\* Substrate Failure

## TYPICAL ENVIRONMENTAL RESISTANCE

Cured for 24h at 22 °C on Grit Blasted Mild Steel

Lap Shear Strength, ISO 4587

## **HEAT AGING**

Aged at temperature indicated and tested at 22 °C

	Strength (N/mm <sup>2</sup> )
24h at 22 °C	>24
3 days at 120 °C	12 - 14
3 days at 150 °C	4 - 6

## GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS): Part A (242983) and Part B (242984)

### **Directions for use:**

- 1) Before applying the glue, make sure the gluing surface is clean, dry and free of grease.
- 2) To assemble the syringe, first introduce the plunger, then exchange the cap with a mixer. Discard the first few drops.
- 3) Apply the material on one of the two surfaces and assemble the two parts within 15 minutes.
- 4) After uniting the substrates, 15-30 seconds are available for repositioning depending on the substrate. Press the two parts together firmly for around 30 seconds. After releasing the pressure, wait 20 minutes before good handling strength and 24h for full strength.
- 5) Make use of the syringe or discard product at least every 40 minutes to avoid the product from polymerizing inside the mixer, if you do not want to replace the mixer.
- 6) After use, discard the mixer and replace the cap. Store the syringe in a cool and dry environment.
- 7) Optimal storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.
- 8) Product shelf-life: 12 months

### **Conversions:**

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{in}$$

$$\mu\text{m} / 25.4 = \text{mil}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{N/mm}^2 \times 145 = \text{psi}$$

$$\text{MPa} \times 145 = \text{psi}$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

### **NOTE**

The data contained herein are furnished for information only and are believed to be reliable. AFINITICA cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, AFINITICA Technologies s.l. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of AFINITICA's products. AFINITICA specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any AFINITICA Technologies patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.